

# PRODUCT DATA SHEET



Client :	<b>Portland Stone Firms Limited</b>
Address:	99 Easton Street, , Portland, Dorset, DT5 1BP.
Client Reference:	<b>Perryfield Roach</b>
Data Prepared By :	<b>ACS Testing Limited</b>
Address:	Unit 14 Blackhill Road West, Holton Heath Trading Park, Poole, Dorset, BH16 6LE Tel 01202 622858 Fax 01202 625045

ACS Test Ref.	Test Description (Test Method)	Result	Units	Date	
M71	Determination of resistance to salt crystallization (BS EN 12370:1999)	Mean Mass Change	-14.6	%	Jan 2012
M72	Determination of frost resistance (BS EN 12371:2010)	Change in Performance	-42.9	%	Feb 2012
M73	Determination of flexural strength under concentrated load (BS EN 12372:2006)	Flexural Strength $R_{ff}$	ND*	MPa	N/A
M73i	Frost Resistance - Determination of flexural strength under concentrated load (BS EN 12372:2006)	Flexural Strength $R_{ff}$ (after Frost Cycles)	ND*	MPa	N/A
M74	Determination of petrographic examination (BS EN 12407:2007)	Limestone Biomicrite	Description	Jan 2012	
M75	Determination of flexural strength under constant moment (BS EN 13161:2008)	Flexural Strength $R_{tc}$	3.5	MPa	Dec 2011
M75i	Frost Resistance - Determination of flexural strength under constant moment (BS EN 13161:2008)	Flexural Strength $R_{tc}$ (after Frost Cycles)	2.0	MPa	Feb 2012
M76	Determination of breaking load at dowel hole (BS EN 13364:2002)	Mean Breaking Load	ND*	N	N/A
M77	Determination of water absorption at atmospheric pressure (BS EN 13755:2008)	Mean Water Absorption	4.7	%	Jan 2012
M78	Determination of abrasion resistance (BS EN 14157:2004)	Mean Groove Length	20.5	mm	Dec 2011
M79dry	Determination of slip resistance by pendulum tester (BS EN 14231:2003)	SRV "DRY" =	76	nr.	Dec 2011
M79wet	Determination of slip resistance by pendulum tester (BS EN 14231:2003)	SRV "WET" =	69	nr	Dec 2011
M80	Determination of water absorption coefficient by capillarity(BS EN 1925:1999)	Absorption Coefficient. (Perpendicular to plane of Anisotropy)	23.5	$g/m^2.s^{0.5}$	Feb 2012
M80	Determination of water absorption coefficient by capillarity(BS EN 1925:1999)	Absorption Coefficient. (Parallel with plane of Anisotropy)	20.2	$g/m^2.s^{0.5}$	Feb 2012
M81	Determination of uniaxial compressive strength (BS EN 1926:2006)	Compressive Strength R	38	MPa	Dec 2011
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Real Density	2690	$kg/m^3$	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Apparent Density	2330	$kg/m^3$	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Open Porosity	13.7	%	Jan 2012
M82	Determination of real & apparent density, and total & open porosity (BS EN 1936:2006)	Total Porosity	13.7	%	Jan 2012

Notes: ND* = Not Determined/Requested	Approved :	Date : 14/04/2012
--	------------	-------------------

Approved Signatories :  
 S J White Head of Laboratories [ ] A Bates Laboratory Manager [ ] K Tiller Technical Manager [  ] M Slater Senior Technician